

Test Liner 1

Typical Values	Method	Unit of measurement	Tolerance	Substance (G/M2)						
				80	90	100	115	125	140	150
Burst	T807	Kpa	10%	230	250	270	310	330	360	380
Sct	T826	KN/m	10%	1.3	1.5	1.7	2.1	2.3	2.4	2.5
Rct	T822	Kgf	10%	14	16	18	22	25	28	30
Cobb 60	T441	G/m2	10%	35	35	35	35	35	35	35
Thickness	T411	µm	10%	153	157	164	170	190	200	220
Moisture	Online / T412	%	10%	7	7	7	7	7	7	7

- Test conditions: Typical values after conditioning, measured at **50 ± 2% RH and 23 ± 1°**

- ✓ Nile paper top kraft will provide the highest strength and print properties
- ✓ and combined with optimum runability in your process .

